

MARKED-UP VERSION OF AMENDED CLAIMS

8. (Amended) [The] A magnetic recording medium [according to claim 1 which is] including a lower non-magnetic layer containing at least a carbon black and a radiation curing type binder resin on a non-magnetic support and an upper magnetic layer having a thickness of 0.30 μm or less on the lower non-magnetic layer, the upper magnetic layer containing at least a ferromagnetic powder, a binder resin, and an abrasive having a Mohs hardness of 6 or higher and a smaller average particle size than the thickness of the upper magnetic layer, the magnetic recording medium produced by [the] a process [according to claim 6 or 7] comprising the steps of:

preparing respectively a lower non-magnetic layer coating material including at least the carbon black dispersed into the radiation curing type binder resin, and an upper magnetic layer coating material including at least the ferromagnetic powder, and the abrasive to be formed into a binder resin,

applying the lower non-magnetic layer coating material onto a non-magnetic support, drying the coating material, and carrying out a smoothing treatment of and irradiating with radiation to a resulting layer to form the lower non-magnetic layer, and then

applying the upper magnetic layer coating material onto the lower non-magnetic layer, drying the coating material, and carrying out the smoothing treatment of the resulting layer to form the upper magnetic layer.

20250507 041802